

PolyOne Edgetek® AT-15GF/000 Acetal-Copolymer, Glass Filled (discontinued **)

Category : Polymer , Thermoplastic , Acetal (POM)

Material Notes:

Description/Features: Glass Fiber Reinforced Information provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-AT-15GF000-Acetal-Copolymer-Glass-Filled-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.51 g/cc	1.51 g/cc	ASTM D792
Water Absorption	0.0010 %	0.0010 %	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0055 - 0.0070 cm/cm	0.0055 - 0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.7 MPa	8800 psi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	4.14 GPa	600 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	75.8 MPa	11000 psi	ASTM D790
Flexural Modulus	4.14 GPa	600 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.30 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	193 - 216 °C	380 - 420 °F	Molding
Mold Temperature	60.0 - 71.1 °C	140 - 160 °F	
Drying Temperature	71.1 °C	160 °F	
Dry Time	2 hour	2 hour	

Descriptive Properties	Value	Comments
Product Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China