

PolyOne Edgetek® XT X XT 1000 Natural Copolyester

Category : Polymer , Thermoplastic , Polyester, TP

Material Notes:

Edgetek™ XT high performance blends offer outstanding strength, durability and chemical resistance through the combination of Eastman Tritan™ copolyester with other various polymeric resins. Edgetek™ XT blends made with Tritan™ copolyester are available in standard grades or can be customized to meet specific performance requirements. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-XT-X-XT-1000-Natural-Copolyester.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.16 g/cc	1.16 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0058 cm/cm @Thickness 3.18 mm	0.0058 in/in @Thickness 0.125 in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0030 cm/cm @Thickness 3.18 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	22 g/10 min @Load 5.00 kg, Temperature 260 °C	22 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	36.5 MPa	5290 psi	Type I, 51 mm/min; ASTM D638
Tensile Strength, Yield	40.0 MPa	5800 psi	51 mm/min; ASTM D638
Elongation at Break	74 %	74 %	Type I, 51 mm/min; ASTM D638
Tensile Modulus	1.56 GPa	226 ksi	Type I, 51 mm/min; ASTM D638
Flexural Strength	72.4 MPa	10500 psi	13 mm/min; ASTM D790
Flexural Modulus	1.72 GPa	249 ksi	13 mm/min; ASTM D790
Izod Impact, Notched	9.60 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	18.0 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	71.0 µm/m-°C @Temperature -30.0 - 30.0 °C	39.4 µin/in-°F @Temperature -22.0 - 86.0 °F	ASTM D696

Thermal Properties (50 psi)	95.0 °C Metric	203 °F English	Comments
Deflection Temperature at 0.46 MPa	@Thickness 3.18 mm	@Thickness 0.125 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C @Thickness 3.18 mm	176 °F @Thickness 0.125 in	Unannealed; ASTM D648

Descriptive Properties	Value	Comments
Features	BPA Free	
	Cleanable	
	Good Chemical Resistance	
	Good Color Stability	
	Good Processability	
	Good Toughness	
	High Impact Resistance	
	Hydrolytically Stable	
	Medium Heat Resistance	
Forms	Pellets	
Generic Material	Copolyester	
Generic Name	Copolyester	
Regional Availability	Africa & Middle East	
	Europe	
	North America	
	South America	
Uses	Appliance Components	
	Appliances	
	Consumer Applications	
	Electrical Housing	
	Household Goods	
	Housings	
	Industrial Applications	

Descriptive Properties	Value:ware	Comments
	Medical Appliances	
	Medical/Healthcare Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China