

## PolyOne Elastamax™ EG-9165 Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

The Elastamax™ EG 9100 Series is a new family of olefin-based TPE compounds offering outstanding elastomeric performance in a lightweight and easy to process material. The EG 9100 Series of compounds feature unique high melt strength and shear thinning characteristics compared to conventional TPE materials for enhanced processability in extrusion applications. Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Elastamax-EG-9165-Thermoplastic-Elastomer-TPE.php](http://www.lookpolymers.com/polymer_PolyOne-Elastamax-EG-9165-Thermoplastic-Elastomer-TPE.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.878 g/cc	0.878 g/cc	ASTM D792
Melt Flow	11 g/10 min @Load 5.00 kg, Temperature 190 °C	11 g/10 min @Load 11.0 lb, Temperature 374 °F	Procedure A; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	10 sec; ASTM D2240
	64	64	ASTM D2240
Tensile Stress	3.00 MPa @Strain 100 %	435 psi @Strain 100 %	510 mm/min; ASTM D412A
	3.52 MPa @Strain 200 %	511 psi @Strain 200 %	510 mm/min; ASTM D412A
	4.03 MPa @Strain 300 %	585 psi @Strain 300 %	510 mm/min; ASTM D412A
Tensile Strength, Yield	4.24 MPa	615 psi	510 mm/min; ASTM D412A
Elongation at Break	460 %	460 %	510 mm/min; ASTM D412A
Tear Strength	35.0 kN/m	200 pli	Die C, 510 mm/min; ASTM D624

Descriptive Properties	Value	Comments
Features	General Purpose	
	Good Melt Strength	
Forms	Pellets	

<b>Generic Material Descriptive Properties</b>	<b>TPE Value</b>	<b>Comments</b>
<b>Generic Name</b>	Thermoplastic Elastomer (TPE)	
<b>Processing Method</b>	Blow Molding	
	Extrusion	
	Foam Extrusion	
	Profile Extrusion	
	Sheet Extrusion	
<b>Regional Availability</b>	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
<b>Uses</b>	Automotive Applications	
	Construction Applications	
	Consumer Applications	
	General Purpose	
	Industrial Applications	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China