

## PolyOne Elastamax™ HTE 1109 Styrene Butadiene Block Copolymer (SBC) with Mineral Filler (discontinued \*\*)

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Elastamax-HTE-1109-Styrene-Butadiene-Block-Copolymer-SBC-with-Mineral-Filler-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_PolyOne-Elastamax-HTE-1109-Styrene-Butadiene-Block-Copolymer-SBC-with-Mineral-Filler-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.79 g/cc	1.79 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	ASTM D2240
	@Time 5.00 sec	@Time 0.00139 hour	
Tensile Strength at Break	1.64 MPa	238 psi	510 mm/min; ASTM D412A
Elongation at Break	110 %	110 %	510 mm/min; ASTM D412A
Tear Strength	13.1 kN/m	74.7 pli	Die C, 510 mm/min; ASTM D624

Descriptive Properties	Value	Comments
Features	General Purpose	
Forms	Pellets	
Generic Name	Styrene Butadiene Block Copolymer (SBC)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Automotive Interior Parts	
	Consumer Applications	
	General Purpose	
	Industrial Applications	

Descriptive Properties	Value	Comments
------------------------	-------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China