

PolyOne Elastamax™ XL-0153-56 Styrene Butadiene Block Copolymer (SBC) (discontinued **)

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

Material Notes:

A thermoplastic elastomer compound formulated for use in food contact applications. The physical properties listed above are typical values obtained on laboratory prepared samples and tested in accordance with accepted test methods. All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21 for use in the packaging of food. The listings cover many uses and restrictions may apply depending on the application. For More Information contact PolyOne.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Elastamax-XL-0153-56-Styrene-Butadiene-Block-Copolymer-SBC-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.958 g/cc	0.958 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	43	43	ASTM D2240
	@Time 5.00 sec	@Time 0.00139 hour	
Tensile Strength at Break	7.65 MPa	1110 psi	510 mm/min; ASTM D412A
Tensile Strength, Yield	1.86 MPa	270 psi	510 mm/min; ASTM D412A
	@Strain 100 %	@Strain 100 %	
Elongation at Break	3.72 MPa	540 psi	510 mm/min; ASTM D412A
	@Strain 300 %	@Strain 300 %	

Descriptive Properties	Value	Comments
Agency Ratings	FDA Food Contact, Unspecified Rating	
Features	Food Contact Acceptable	
	General Purpose	
Forms	Pellets	
Generic Name	Styrene Butadiene Block Copolymer (SBC)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	

Descriptive Properties	Value	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Consumer Applications	
	General Purpose	
	Overmolding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China