

PolyOne Elastamax™ XL-0203-12 Styrene Butadiene Block Copolymer (SBC) (discontinued **)

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Elastamax-XL-0203-12-Styrene-Butadiene-Block-Copolymer-SBC-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	ASTM D2240
	@Time 5.00 sec	@Time 0.00139 hour	
Tensile Strength at Break	6.48 MPa	940 psi	510 mm/min; ASTM D412A
Tensile Strength, Yield	4.17 MPa	605 psi	510 mm/min; ASTM D412A
	@Strain 100 %	@Strain 100 %	
Elongation at Break	260 %	260 %	510 mm/min; ASTM D412A
Tear Strength	26.3 kN/m	150 pli	Die C, 510 mm/min; ASTM D624

Descriptive Properties	Value	Comments
Features	General Purpose	
Forms	Pellets	
Generic Name	Styrene Butadiene Block Copolymer (SBC)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Consumer Applications	
	General Purpose	

Descriptive Properties	Overmolding Value	Comments
------------------------	-------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China