

PolyOne Elastamax™ XL-2085 Thermoplastic Polyolefin Elastomer (TPO (POE))

Category : Polymer , Thermoplastic , Elastomer, TPE , Olefinic TPE

Material Notes:

PolyOne's Elastamax™ XL thermoplastic olefins (TPOs) are based on pelletized blends of polyolefin resins and select elastomers such as EPDM. These materials have been engineered to provide a balance of physical properties and processability, and are an economical alternative to traditional thermoset rubber and more costly thermoplastic elastomers. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Elastamax-XL-2085-Thermoplastic-Polyolefin-Elastomer-TPO-POE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	91	91	15 sec; ASTM D2240
	94	94	ASTM D2240
Tensile Strength at Break	8.27 MPa	1200 psi	510 mm/min; ASTM D412A
Tensile Stress	5.52 MPa	801 psi	510 mm/min; ASTM D412A
	@Strain 100 %	@Strain 100 %	
	6.07 MPa	880 psi	510 mm/min; ASTM D412A
	@Strain 300 %	@Strain 300 %	
Elongation at Break	610 %	610 %	510 mm/min; ASTM D412A
Tear Strength	50.4 kN/m	288 pli	Die C, 510 mm/min; ASTM D624
Compression Set	54 %	54 %	ASTM D395B
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	

Descriptive Properties	Value	Comments
Additive	UV Stabilizer	
Features	General Purpose	
Forms	Pellets	
Generic Material	TPO (POE)	
Generic Name	Thermoplastic Polyolefin Elastomer (TPO (POE))	
Processing Method	Injection Molding	

Descriptive Properties	Value	Comments
Regional Availability	Asia & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Construction Applications	
	General Purpose	
	Industrial Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China