

PolyOne FireCon™ CPE 30-11 RoHS BLACK Polyethylene, Chlorinated (CPE)

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

CPE-30-11 RoHS BLACK is a heavy duty thermoplastic jacket for power and control cables. It is suitable for VW1 and tray fire rated applications. CPE-30-11 RoHS BLACK offers high tensile and superior fluid resistance. Note: Pre-drying is recommended for 4 hours at 175°-185°F. Note: Typical processing temperatures range between 320°-390°F depending upon screw design. Contact Technical Service for recommendation for specific equipment. NOTE: Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-FireCon-CPE-30-11-RoHS-BLACK-Polyethylene-Chlorinated-CPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.29 g/cc	1.29 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	41	41	10 sec; ASTM D2240
Tensile Strength at Break	11.7 MPa	1700 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	350 %	350 %	Type IV, 510 mm/min; ASTM D638
Tensile Modulus	0.00827 GPa	1.20 ksi	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-35.0 °C	-31.0 °F	ASTM D746
Oxygen Index	30 % @Thickness 1.91 mm	30 % @Thickness 0.0752 in	ASTM D2863

Descriptive Properties	Value	Comments
Appearance	Pellets/Cubes	ASTM D2090
Features	Flame Retardant	
Forms	Pellets	
Generic Material	CPE	
Generic Name	Polyethylene, Chlorinated (CPE)	
Regional Availability	Asia Pacific	
	North America	

Descriptive Properties	Value <small>America</small>	Comments
RoHS Compliance	RoHS Compliant	
Uses	Cable Jacketing	
	Wire & Cable Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China