

## PolyOne Geon™ 170 Series 173 Polyvinyl Chloride Homopolymer (PVC Homopolymer)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Note: Plastisol Formulation F1 consists of 100 parts of this resin + 60 parts DOP. Note: Plastisol Formulation F2 consists of 100 parts of this resin + 57 parts DOP + 3 parts ESO + 2 parts Synpron® 940. Note: The values set forth represent typical values and PolyOne Corporation, therefore, makes no representation that the material in any particular shipment will conform to the listed properties.

Packaging: This resin is shipped in multi-wall paper bags, net weight 50 lbs, 2500 lbs per pallet. Information shown on the package includes commercial identification number, lot and weight. Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-170-Series-173-Polyvinyl-Chloride-Homopolymer-PVC-Homopolymer.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-170-Series-173-Polyvinyl-Chloride-Homopolymer-PVC-Homopolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Density	0.320 - 0.400 g/cc	0.0116 - 0.0145 lb/in <sup>3</sup>	ASTM D1505
Fineness	5.5	5.5	North Fineness; Geon® 390
Relative Viscosity	2.37 cP	2.37 cP	1% Cyclohexanone
Brookfield Viscosity	2.55 cP	2.55 cP	Initial, V12, Geon® 1010
	3.6 cP	3.6 cP	One Day, V12, Geon® 1010
Viscosity Measurement	1.0	1.0	Inherent; ASTM D1243-60-A
Melt Flow	270 g/10 min	270 g/10 min	Severs Efflux; Geon® 1010
	@Pressure 0.655 MPa	@Pressure 95.0 psi	

Mechanical Properties	Metric	English	Comments
Tensile Strength	16.5 MPa	2390 psi	Optimum; FF; ASTM D638
Elongation at Yield	350 %	350 %	FF; Optimum Tensile; ASTM D412

Optical Properties	Metric	English	Comments
Gloss	93 %	93 %	60°, FF, ALTC-65
Transmission, Visible	86 %	86 %	FF, ATLC-66

Processing Properties	Metric	English	Comments
Moisture Content	0.050 %	0.050 %	Karl Fisher-Geon® 683

Descriptive Properties	Value	Comments
Degree of Polymerization	1250	Correlation
Features	Low to No Odor	
	Low to No Taste	
	Resilient	
Forms	Powder	
Gel Temperature	79 °C	FF, ALTC-29
Generic Material	PVC Homopolymer	
Generic Name	Polyvinyl Chloride Homopolymer (PVC Homopolymer)	
K-Value	69	No Standard; Correlation
Methanol Extractables	1.1%	Geon® 894
Polymerization Process	Dispersion	
Processing Method	Casting	
	Dip Coating	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Coating Applications	
	Film	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China