

## PolyOne Geon™ 80530 Polyvinyl Chloride, Rigid (PVC, Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-80530-Polyvinyl-Chloride-Rigid-PVC-Rigid.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-80530-Polyvinyl-Chloride-Rigid-PVC-Rigid.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.54 g/cc	1.54 g/cc	ASTM D792
Spiral Flow	66.0 cm	26.0 in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	85	85	ASTM D2240
Tensile Strength, Yield	86.2 MPa	12500 psi	Type I, 51 mm/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type I, 51 mm/min; ASTM D638
Tensile Modulus	8.62 GPa	1250 ksi	Type I, 51 mm/min; ASTM D638
Flexural Strength	145 MPa	21000 psi	ASTM D790
Flexural Modulus	7.93 GPa	1150 ksi	ASTM D790
Poissons Ratio	0.42	0.42	ASTM E132
Shear Modulus	3.04 GPa	441 ksi	Calculated
Izod Impact, Notched	1.10 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	2.06 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A
Izod Impact, Unnotched	4.30 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	8.06 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	18.0 µm/m-°C	10.0 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	76.1 °C @Thickness 6.35 mm	169 °F @Thickness 0.250 in	Annealed; ASTM D648
UL RTI, Electrical	50.0 °C	122 °F	UL 746
UL RTI, Mechanical with Impact	50.0 °C	122 °F	UL 746

Thermal Properties <small>UL 94, Mechanical without Impact</small>	Metric <small>300 °C</small>	English <small>120 °F</small>	Comments <small>UL 94</small>
Flammability, UL94	V-0	V-0	ALL; UL 94
	@Thickness 1.47 mm	@Thickness 0.0579 in	
	V-0	V-0	All Colors
	@Thickness 1.63 mm	@Thickness 0.0642 in	
	5VA	5VA	ALL; UL 94
	@Thickness 1.47 mm	@Thickness 0.0579 in	
	5VA	5VA	All Colors
	@Thickness 1.63 mm	@Thickness 0.0642 in	

Processing Properties	Metric	English	Comments
Melt Temperature	199 - 210 °C	390 - 410 °F	

Descriptive Properties	Value	Comments
Features	General Purpose	
	High Flow	
Filler / Reinforcement	Glass Fiber Reinforcement, 30% Filler by Weight	
Forms	Pellets	
Generic Material	PVC, Rigid	
Generic Name	Polyvinyl Chloride, Rigid (PVC, Rigid)	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Appliances	
	Business Equipment	
	Construction Applications	
	Electrical/Electronic Applications	
	General Purpose	

Descriptive Properties	Value	Comments
------------------------	-------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China