

PolyOne Geon™ L4605 Green 5765 Polyvinyl Chloride, Semi-Rigid (PVC, Semi-Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-L4605-Green-5765-Polyvinyl-Chloride-Semi-Rigid-PVC-Semi-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75	75	15 sec; ASTM D2240
Tensile Strength, Yield	31.2 MPa	4530 psi	5.1 mm/min; ASTM D638
Tensile Modulus	1.93 GPa	280 ksi	5.1 mm/min; ASTM D638
Flexural Yield Strength	55.9 MPa	8110 psi	13 mm/min; ASTM D790
Flexural Modulus	1.91 GPa	277 ksi	13 mm/min; ASTM D790
Izod Impact, Notched	0.370 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	0.693 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Compression Molded; ASTM D256
Dart Drop Total Energy	69.4 J/cm @Temperature 23.0 °C	0.130 ft-lb/mil @Temperature 73.4 °F	extruded profile, Procedure A, C.125; ASTM D4226
	>= 178 J/cm @Temperature 23.0 °C	>= 0.333 ft-lb/mil @Temperature 73.4 °F	Procedure B, C.125; ASTM D4226

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	75.0 µm/m-°C	41.7 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	42.2 °C @Thickness 3.18 mm	108 °F @Thickness 0.125 in	Annealed; ASTM D648
	42.8 °C @Thickness 3.18 mm	109 °F @Thickness 0.125 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	36.1 °C @Thickness 3.18 mm	97.0 °F @Thickness 0.125 in	Annealed; ASTM D648

Thermal Properties	Metric	English	Comments
	@Thickness 3.18 mm	@Thickness 0.125 in	Unannealed; ASTM D548

Optical Properties	Metric	English	Comments
Gloss	5.0 - 30 %	5.0 - 30 %	60°; ASTM D523

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 193 °C	360 - 379 °F	

Descriptive Properties	Value	Comments
Features	Medium Gloss	
Forms	Pellets	
Generic Material	PVC, Semi-Rigid	
Generic Name	Polyvinyl Chloride, Semi-Rigid (PVC, Semi-Rigid)	
Processing Method	Coextrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Capstock	
	Outdoor Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China