

PolyOne Geon™ Vinyl Fittings 210A White 271(HS) Polyvinyl Chloride, Rigid (PVC, Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Fittings-210A-White-271HS-Polyvinyl-Chloride-Rigid-PVC-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	ASTM D2240
Tensile Strength, Yield	48.6 MPa	7050 psi	Type I, 51 mm/min; ASTM D638
Tensile Modulus	2.81 GPa	408 ksi	Type I, 51 mm/min; ASTM D638
Flexural Strength	82.0 MPa	11900 psi	ASTM D790
Flexural Modulus	3.02 GPa	438 ksi	ASTM D790
Izod Impact, Notched	0.800 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	1.50 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	71.1 °C @Thickness 6.35 mm	160 °F @Thickness 0.250 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	199 - 210 °C	390 - 410 °F	

Descriptive Properties	Value	Comments
Agency Ratings	NSF 14	
	NSF 61	
	NSF Type I	

Features

Descriptive Properties	High Flow Value	Comments
Forms	Pellets	
Generic Material	PVC, Rigid	
Generic Name	Polyvinyl Chloride, Rigid (PVC, Rigid)	
Processing Method	Injection Molding	
PVC Cell Classification	12454	ASTM D1784
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Fittings	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China