

PolyOne Geon™ Vinyl Fittings M1015 Polyvinyl Chloride, Rigid (PVC, Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Fittings-M1015-Polyvinyl-Chloride-Rigid-PVC-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.42 g/cc	1.42 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	ASTM D955
Spiral Flow	68.6 cm	27.0 in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	81	81	ASTM D2240
Tensile Strength, Yield	52.4 MPa	7600 psi	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	2.96 GPa	429 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	85.5 MPa @Thickness 3.18 mm, Temperature 23.0 °C	12400 psi @Thickness 0.125 in, Temperature 73.4 °F	ASTM D790
Flexural Modulus	2.96 GPa @Thickness 3.18 mm, Temperature 23.0 °C	429 ksi @Thickness 0.125 in, Temperature 73.4 °F	ASTM D790
Izod Impact, Notched	0.600 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	1.12 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	70.6 °C @Thickness 3.18 mm	159 °F @Thickness 0.125 in	Annealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	199 - 210 °C	390 - 410 °F	

Descriptive Properties	Value	Comments
Agency Ratings	NSF 14	

Descriptive Properties	Value	Comments
	NSF Type I	
Features	Medium Flow	
Forms	Pellets	
Generic Material	PVC, Rigid	
Generic Name	Polyvinyl Chloride, Rigid (PVC, Rigid)	
Processing Method	Injection Molding	
PVC Cell Classification	12454	ASTM D1784
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Fittings	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China