

PolyOne Geon™ Vinyl Flexible 90004 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Automotive OEM approval(s).Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-90004-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ASTM D792
Volatiles	0.31 %	0.31 %	Loss; Method A; ASTM D1203B
	@Thickness 1.91 mm, Temperature 105 °C	@Thickness 0.0752 in, Temperature 221 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	92	92	15 sec; ASTM D2240
Tensile Strength at Break	21.0 MPa	3050 psi	510 mm/min; ASTM D638
Elongation at Break	330 %	330 %	510 mm/min; ASTM D638
Tear Strength	72.3 kN/m	413 pli	Die C, 2 in/min; ASTM D1004

Descriptive Properties	Value	Comments
Cold Flexibility	Pass	GM 9503P; -30°C, 1.91 mm; 25 mm, 4 hr
Features	Low Gloss	
Forms	Pellets	
Fungal Resistance	Pass	ASTM G21
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	

Descriptive Properties	Value	Comments
Uses	Automotive Applications	
	Outdoor Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China