

PolyOne Geon™ Vinyl Flexible A7500 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Recommended for interior applications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-A7500-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.019 - 0.023 cm/cm	0.019 - 0.023 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	15 sec; ASTM D2240
	75	75	ASTM D2240
Tensile Strength at Break	13.8 MPa	2000 psi	510 mm/min; ASTM D638
Tensile Strength	5.86 MPa @Strain 100 %	850 psi @Strain 100 %	510 mm/min; ASTM D638
Elongation at Break	400 %	400 %	510 mm/min; ASTM D638
Tear Strength	43.8 kN/m	250 pli	Die C, 510 mm/min; ASTM D624
Compression Set	30 % @Temperature 23.0 °C, Time 79200 sec	30 % @Temperature 73.4 °F, Time 22.0 hour	ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-43.9 °C	-47.0 °F	ASTM D746

Optical Properties	Metric	English	Comments
Haze	4.0 %	4.0 %	ASTM D1003
	@Thickness 1.91 mm	@Thickness 0.0750 in	
Transmission, Visible	82 %	82 %	ASTM D1003
	@Thickness 1.91 mm	@Thickness 0.0750 in	

Processing Properties	Metric	English	Comments
Melt Temperature	174 - 179 °C	345 - 354 °F	

Processing Properties	Metric	English	Comments
	193 - 204 °C	379 - 399 °F	

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	
Features	General Purpose	
	High Gloss	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	General Purpose	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China