

PolyOne Geon™ Vinyl Flexible C70UB Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-C70UB-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	64	64	15 sec; ASTM D2240
	70	70	ASTM D2240
Tensile Strength at Break	9.65 MPa	1400 psi	Type IV, 510 mm/min; ASTM D638
Tensile Strength	4.34 MPa	629 psi	Type IV, 510 mm/min; ASTM D638
	@Strain 100 %	@Strain 100 %	
Elongation at Break	390 %	390 %	Type IV, 510 mm/min; ASTM D638
Tear Strength	35.0 kN/m	200 pli	Die C, 510 mm/min; ASTM D624
Compression Set	20 %	20 %	ASTM D395
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	
Clash Berg Modulus	0.0814 GPa	11.8 ksi	ASTM D1043
	0.310 GPa	45.0 ksi	ASTM D1043
	@Temperature -46.0 °C	@Temperature -50.8 °F	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-42.2 °C	-44.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	171 - 177 °C	340 - 351 °F	
	193 - 199 °C	379 - 390 °F	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Additive Descriptive Properties	Bioicide Value	Comments
	UV Stabilizer	
Features	Medium Gloss	
	UV Absorbing	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Coextrusion	
	Extrusion	
	Injection Molding	
	Profile Extrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China