

## PolyOne Geon™ Vinyl Flexible D7500 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-D7500-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-D7500-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc	1.48 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	15 sec; ASTM D2240
	75	75	ASTM D2240
Tensile Strength at Break	7.93 MPa	1150 psi	510 mm/min; ASTM D638
Tensile Strength	4.83 MPa @Strain 100 %	701 psi @Strain 100 %	510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	510 mm/min; ASTM D638
Tear Strength	31.5 kN/m	180 pli	Die C, 510 mm/min; ASTM D624
Compression Set	30 % @Temperature 23.0 °C, Time 79200 sec	30 % @Temperature 73.4 °F, Time 22.0 hour	ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-37.8 °C	-36.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	174 - 179 °C	345 - 354 °F	

Descriptive Properties	Value	Comments
Features	General Purpose	
	Low Gloss	
Forms	Pellets	
Generic Material	PVC, Flexible	

<b>Generic Name</b> Descriptive Properties	<b>Polyvinyl Chloride, Flexible (PVC, Flexible)</b> Value	Comments
Processing Method	Extrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	General Purpose	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China