

PolyOne Geon™ Vinyl Flexible F80E Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-F80E-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	15 sec; ASTM D2240
Tensile Strength at Break	15.9 MPa	2310 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-35.0 °C	-31.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	138 - 149 °C	280 - 300 °F	

Descriptive Properties	Value	Comments
Additive	Barium-Zinc Stabilizer	
Features	General Purpose	
	Good Melt Strength	
	Low Hardness	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	

Descriptive Properties	Europe Value	Comments
	North America	
	South America	
Uses	General Purpose	
	Purging Compound	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China