

PolyOne Geon™ Vinyl Flexible FC800 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:
http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-FC800-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	Inst. Hardness +/- 5 units.; ASTM D2240
Tensile Strength at Break	12.5 MPa	1810 psi	510 mm/min; ASTM D638
Elongation at Break	340 %	340 %	510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-37.2 °C	-35.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	177 - 182 °C	351 - 360 °F	
	191 - 196 °C	376 - 385 °F	

Descriptive Properties	Value	Comments
Features	General Purpose	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	Value America	Comments
	South America	
Uses	General Purpose	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China