

PolyOne Geon™ Vinyl Flexible G8024 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-G8024-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	77	77	15 sec; ASTM D2240
Tensile Strength at Break	17.1 MPa	2480 psi	Type IV, 510 mm/min; ASTM D638
Tensile Strength	10.3 MPa @Strain 100 %	1490 psi @Strain 100 %	Type IV, 510 mm/min; ASTM D638
Elongation at Break	320 %	320 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-32.8 °C	-27.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	177 - 182 °C	351 - 360 °F	
	188 - 199 °C	370 - 390 °F	

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	
Features	High Clarity	
	High Gloss	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	

Descriptive Properties	Injection Molding Value	Comments
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Furniture	
	Hose	
	Tubing	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China