

## PolyOne Geon™ Vinyl Flexible H43356A Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-H43356A-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-H43356A-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	56	56	15 sec; ASTM D2240
Tensile Strength at Break	4.83 MPa	701 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-31.1 °C	-24.0 °F	ASTM D746
Oxygen Index	22 % @Thickness 3.18 mm	22 % @Thickness 0.125 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	168 - 174 °C	334 - 345 °F	

Descriptive Properties	Value	Comments
Features	Low Gloss	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	Value	Comments
	North America	
	South America	
Uses	Construction Applications	
	Gaskets	
	Seals	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China