

## PolyOne Geon™ Vinyl Flexible R109AM Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-R109AM-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R109AM-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	67	67	15 sec; ASTM D2240
Tensile Strength at Break	14.5 MPa	2100 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	400 %	400 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-37.2 °C	-35.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	171 - 177 °C	340 - 351 °F	
	182 - 188 °C	360 - 370 °F	

Descriptive Properties	Value	Comments
Features	High Flow	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	

Descriptive Properties	Europe Value	Comments
	North America	
	South America	
Uses	Footwear	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China