

PolyOne Geon™ Vinyl Flexible R132BE Polyvinyl Chloride + NBR (PVC+NBR)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R132BE-Polyvinyl-Chloride-NBR-PVCNBR.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	81	81	15 sec; ASTM D2240
Tensile Strength at Break	15.2 MPa	2200 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	380 %	380 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-23.9 °C	-11.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	185 - 191 °C	365 - 376 °F	
	193 - 204 °C	379 - 399 °F	

Descriptive Properties	Value	Comments
Additive	Biocide	
Features	Low Compression Set	
Forms	Pellets	
Generic Material	PVC+NBR	
Generic Name	Polyvinyl Chloride + NBR (PVC+NBR)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	

Descriptive Properties	Europe Value	Comments
	North America	
	South America	
Uses	Footwear	
	Hose	
	Marine Applications	
	Tubing	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China