

## PolyOne Geon™ Vinyl Flexible R252BE Polyvinyl Chloride + NBR (PVC+NBR)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-R252BE-Polyvinyl-Chloride-NBR-PVCNBR.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R252BE-Polyvinyl-Chloride-NBR-PVCNBR.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.29 g/cc	1.29 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	83	83	15 sec; ASTM D2240
Tensile Strength at Break	15.9 MPa	2310 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	350 %	350 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-32.2 °C	-26.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	177 - 182 °C	351 - 360 °F	
	193 - 204 °C	379 - 399 °F	

Descriptive Properties	Value	Comments
Additive	Biocide	
	UV Stabilizer	
Features	UV Absorbing	
Forms	Pellets	
Generic Material	PVC+NBR	
Generic Name	Polyvinyl Chloride + NBR (PVC+NBR)	
Processing Method	Coextrusion	
	Extrusion	
	Injection Molding	

Regional Availability Descriptive Properties	Africa & Middle East Value	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Flooring	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China