

PolyOne Geon™ Vinyl Flexible R323AE Polyvinyl Chloride Elastomer (PVC Elastomer)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R323AE-Polyvinyl-Chloride-Elastomer-PVC-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.28 g/cc	1.28 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	69	69	15 sec; ASTM D2240
Tensile Strength at Break	16.5 MPa	2390 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	400 %	400 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-48.9 °C	-56.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	171 - 182 °C	340 - 360 °F	
	188 - 199 °C	370 - 390 °F	

Descriptive Properties	Value	Comments
Additive	Biocide	
Features	Good Adhesion	
Forms	Pellets	
Generic Material	PVC Elastomer	
Generic Name	Polyvinyl Chloride Elastomer (PVC Elastomer)	
Processing Method	Coextrusion	
	Extrusion	
	Injection Molding	

Regional Availability Descriptive Properties	Africa & Middle East Value	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Construction Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China