

## PolyOne Geon™ Vinyl Flexible XV 3432 Trans 9000 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

This product has received full compliance certification for USP Biological Reactivity Tests under USP Plastic Class VI. NOTE: All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21. The only restriction is that the plasticizer is For foods of high water content only. This statement is only an overview of the FDA listings for this product. It is the customer's responsibility to ensure that the compound is suitable for its intended application. Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-XV-3432-Trans-9000-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-XV-3432-Trans-9000-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	10 sec; ASTM D2240
Tensile Strength at Break	18.6 MPa	2700 psi	Type IV, 510 mm/min; ASTM D638
Tensile Strength	12.4 MPa @Strain 100 %	1800 psi @Strain 100 %	Type IV, 510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-25.0 °C	-13.0 °F	ASTM D746

Descriptive Properties	Value	Comments
Agency Ratings	FDA Food Contact, Unspecified Rating	
Appearance	Clear/Transparent	
Features	Food Contact Acceptable	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion Injection Molding	

Descriptive Properties	Value & Middle East	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Hose	
	Tubing	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China