

## PolyOne Geon™ Vinyl Flexible XV3437 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category: Polymer, Thermoplastic, Vinyl (PVC)

## **Material Notes:**

All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21. The only restriction is that the plasticizer is For foods of high water content only. This statement is only an overview of the FDA listings for this product. It is the customer's responsibility to ensure that the compound is suitable for its intended application. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer\_PolyOne-Geon-Vinyl-Flexible-XV3437-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.26 g/cc	1.26 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments	
Hardness, Shore A	90	90	10 sec; ASTM D2240	
Tensile Strength at Break	20.7 MPa	3000 psi	Type IV, 510 mm/min; ASTM D638	
Tongila Strongth	15.2 MPa	2200 psi	T IV 510 ( AOTM DC20	
Tensile Strength	@Strain 100 %	@Strain 100 %	Type IV, 510 mm/min; ASTM D638	
Elongation at Break	270 %	270 %	Type IV, 510 mm/min; ASTM D638	

Thermal Properties	Metric	English	Comments	
Brittleness Temperature	-20.0 °C	-4.00 °F	ASTM D746	

Descriptive Properties	Value	Comments
Agency Ratings	FDA Food Contact, Unspecified Rating	
	USP Class VI	
Appearance	Clear/Transparent	
Features	Food Contact Acceptable	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	



Descriptive Properties	Value on Molding	Comments
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Hose	
	Medical Appliances	
	Tubing	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China