

PolyOne Geon™ Vinyl Flexible XV3758 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category: Polymer, Thermoplastic, Vinyl (PVC)

Material Notes:

All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21. The only restriction is that the plasticizer is For foods of high water content only. This statement is only an overview of the FDA listings for this product. It is the customer's responsibility to ensure that the compound is suitable for its intended application. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-XV3758-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	10 sec; ASTM D2240
Tensile Strength, Yield	15.9 MPa	2310 psi	510 mm/min; ASTM D412A
Elongation at Break	350 %	350 %	510 mm/min; ASTM D412A
Tensile Modulus	0.00621 GPa	0.901 ksi	Method A, 20 in/min; ASTM D412

Thermal Properties	Metric	English	Comments	
Brittleness Temperature	-40.0 °C	-40.0 °F	ASTM D746	

Descriptive Properties	Value	Comments	
Agency Ratings	FDA Food Contact, Unspecified Rating	FDA Food Contact, Unspecified Rating	
	FDA Unspecified Rating		
Appearance	Clear/Transparent		
Features	Food Contact Acceptable		
	High Gloss		
	Radiation (Gamma) Resistant		
Forms	Pellets		
Generic Material	PVC, Flexible		
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)		



Descriptive Properties	Value	Comments
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Hose	
	Medical Appliances	
	Tubing	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China