

## PolyOne Geon™ Vinyl Flexible XV3861 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category: Polymer, Thermoplastic, Vinyl (PVC)

## **Material Notes:**

All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21. The only restriction is that the plasticizer is For foods of high water content only. This statement is only an overview of the FDA listings for this product. It is the customer's responsibility to ensure that the compound is suitable for its intended application. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer\_PolyOne-Geon-Vinyl-Flexible-XV3861-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	59	59	15 sec; ASTM D2240
	60	60	10 sec; ASTM D2240
Tensile Strength at Break	14.0 MPa	2030 psi	Type IV, 510 mm/min; ASTM D638
Tensile Strength	5.24 MPa	760 psi	Type IV, 510 mm/min; ASTM D638
rensile Strength	@Strain 100 %	@Strain 100 %	
Elongation at Break	370 %	370 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-25.0 °C	-13.0 °F	ASTM D746

Descriptive Properties	Value	Comments
Agency Ratings	FDA Unspecified Rating	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Blow Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	



Descriptive Properties	Value =	Comments
	North America	
	South America	
Uses	Bottles	
	Medical Appliances	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China