

## PolyOne Geon™ Vinyl Flexible XV3906 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category: Polymer, Thermoplastic, Vinyl (PVC)

## **Material Notes:**

NOTE: All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21. The only restriction is that the plasticizer is For foods of high water content only. This statement is only an overview of the FDA listings for this product. It is the customer's responsibility to ensure that the compound is suitable for its intended application. This compound has obtained conformance to Cytotoxicity tests under ISO 10993-5 GUIDELINES, when combined with Trans 1756 pigmentation. Information provided by PolyOne

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_PolyOne-Geon-Vinyl-Flexible-XV3906-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	15 sec; ASTM D2240
Tensile Strength at Break	17.2 MPa	2490 psi	Type IV, 510 mm/min; ASTM D638
Tensile Strength	8.27 MPa	1200 psi	Type IV 510 mm/min; ACTM DC20
	@Strain 100 %	@Strain 100 %	Type IV, 510 mm/min; ASTM D638
Elongation at Break	350 %	350 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-35.0 °C	-31.0 °F	ASTM D746

Descriptive Properties	Value	Comments
Agency Ratings	CPSIA Compliant	
	FDA Food Contact, Unspecified Rating	
	ISO 10993 Part 5	
Appearance	Clear/Transparent	
Features	Food Contact Acceptable	
	Non-Phthalate Plasticizer	
Forms	Pellets	



Descriptive Properties	PVC Flexible Value	Comments
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Medical Appliances	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China