

PolyOne Geon™ Vinyl Packaging 2320 LCW Polyvinyl Chloride, Rigid (PVC, Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Packaging-2320-LCW-Polyvinyl-Chloride-Rigid-PVC-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792
Density	0.833 g/cc	0.0301 lb/in ³	ASTM D1505

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	82	82	ASTM D2240
Tensile Strength, Yield	47.6 MPa	6900 psi	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	2.47 GPa	358 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	2.83 GPa	410 ksi	ASTM D790
Izod Impact, Notched	0.530 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	0.993 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	68.3 °C @Thickness 3.18 mm	155 °F @Thickness 0.125 in	Unannealed; ASTM D648

Optical Properties	Metric	English	Comments
Transmission, Visible	84 % @Thickness 0.851 mm, Wavelength 400 nm	84 % @Thickness 0.0335 in, Wavelength 400 nm	Internal Method
	89 % @Thickness 0.851 mm, Wavelength 700 nm	89 % @Thickness 0.0335 in, Wavelength 700 nm	Internal Method

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Mold Temperature Processing Properties	202 - 213 °C Metric	396 - 415 °F English	Blow Molding Comments
---	------------------------	-------------------------	--------------------------

Descriptive Properties	Value	Comments
Agency Ratings	FDA Food Contact, Unspecified Rating	
Appearance	Clear/Transparent	
Features	Food Contact Acceptable	
	High Gloss	
Forms	Pellets	
Generic Material	PVC, Rigid	
Generic Name	Polyvinyl Chloride, Rigid (PVC, Rigid)	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Bottles	
	Packaging	
	Sheet	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China