

PolyOne Geon™ Vinyl Rigid Extrusion 87416 Polyvinyl Chloride, Rigid (PVC, Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

The Cell Classification was determined using the notched Izod test with injection molded samples. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Rigid-Extrusion-87416-Polyvinyl-Chloride-Rigid-PVC-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	82	82	15 sec; ASTM D2240
Tensile Strength, Yield	44.1 MPa	6400 psi	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	2.48 GPa	360 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	84.8 MPa	12300 psi	ASTM D790
Flexural Modulus	2.96 GPa	429 ksi	ASTM D790
Izod Impact, Notched	1.50 J/cm	2.81 ft-lb/in	Compression Molded, Flow; ASTM D256A
	@Thickness 3.18 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	Compression Molded, Across Flow; ASTM D256A
	@Thickness 3.18 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	
Dart Drop Total Energy	53.4 J/cm	0.100 ft-lb/mil	Procedure A, C.125; ASTM D4226
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Dart Drop Total Energy	178 J/cm	0.333 ft-lb/mil	Procedure B, C.125; ASTM D4226
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	61.0 µm/m-°C	33.9 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	72.8 °C	163 °F	Unannealed; ASTM D648
	@Thickness 3.18 mm	@Thickness 0.125 in	
Flammability, UL94	V-0	V-0	ALL; UL 94
	@Thickness 0.749 mm	@Thickness 0.0295 in	

Thermal Properties	Metric	English	Comments
	@Thickness 0.9804 mm	@Thickness 0.03860 in	All Colors

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 193 °C	360 - 379 °F	

Descriptive Properties	Value	Comments
AAMA 303	Pass	ASTM D4726
Agency Ratings	AAMA 303	
Appearance	Colors Available	
Automotive Specifications	CHRYSLER MS-DC28 Type B CPN3012 Color: Black	
	GM GM7001M (PVC)	
Ease of Sizing	Acceptable	
Features	Good Weather Resistance	
	High Impact Resistance	
Forms	Pellets	
Generic Material	PVC, Rigid	
Generic Name	Polyvinyl Chloride, Rigid (PVC, Rigid)	
Processing Method	Extrusion	
PVC Cell Classification	1-31432-33	ASTM D4216
	13344	ASTM D1784
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Automotive Applications	
	Outdoor Applications	

Descriptive Properties	Profiles Value	Comments
Windows & Doors		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China