

PolyOne Geon™ Vinyl Wire & Cable EC486 DA Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-EC486-DA-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	87	87	15 sec; ASTM D2240
Tensile Strength at Break	17.9 MPa	2600 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-45.0 °C	-49.0 °F	ASTM D746
Oxygen Index	26 % @Thickness 3.18 mm	26 % @Thickness 0.125 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	165 - 175 °C	329 - 347 °F	

Descriptive Properties	Value	Comments
Additive	Lead Stabilizer	
Features	Low Temperature Resistant	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	Value	Comments
	North America	
	South America	
Retention of Tensile Elongation	85%	121°C, 1.91 mm; 336 hr, UL Standard
Retention of Tensile Strength	100%	121°C, 1.91 mm; 336 hr, UL Standard
Uses	Insulation	
	Wire & Cable Applications	
Wire Types	TWU	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China