

PolyOne Geon™ Vinyl Wire & Cable JJK501L Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-JJK501L-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82	82	15 sec; ASTM D2240
Tensile Strength, Yield	15.2 MPa	2200 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	280 %	280 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-28.0 °C	-18.4 °F	ASTM D746
Oxygen Index	26 % @Thickness 1.91 mm	26 % @Thickness 0.0752 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	154 - 166 °C	309 - 331 °F	

Descriptive Properties	Value	Comments
Features	Flame Retardant	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion Coating	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	Value	Comments
	North America	
	South America	
Retention of Tensile Elongation	94%	100°C, 1.14 mm; 240 hr, UL Standard
Retention of Tensile Strength	110%	100°C, 1.14 mm; 240 hr, UL Standard
RoHS Compliance	RoHS Compliant	
Uses	Building Wire Jacketing	
	Wire & Cable Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China