

PolyOne Geon™ Vinyl Wire & Cable W1802L-xx17FRD Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-W1802L-xx17FRD-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|-----------|
| Specific Gravity | 1.38 g/cc | 1.38 g/cc | ASTM D792 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|----------|----------|--------------------------------|
| Hardness, Shore A | 92 | 92 | 15 sec; ASTM D2240 |
| Tensile Strength, Yield | 20.7 MPa | 3000 psi | Type IV, 510 mm/min; ASTM D638 |
| Elongation at Break | 290 % | 290 % | Type IV, 510 mm/min; ASTM D638 |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------------------------|------------------------------|-----------------------|
| Maximum Service Temperature, Air | 75.0 °C | 167 °F | UL Temperature Rating |
| Brittleness Temperature | -23.0 °C | -9.40 °F | ASTM D746 |
| Oxygen Index | 31 % @Thickness 1.91 mm | 31 % @Thickness 0.0752 in | ASTM D2863 |

| Processing Properties | Metric | English | Comments |
|-----------------------|--------------|--------------|----------|
| Melt Temperature | 171 - 182 °C | 340 - 360 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|--|----------|
| Additive | UV Stabilizer | |
| Features | Flame Retardant | |
| Forms | Pellets | |
| Generic Material | PVC, Flexible | |
| Generic Name | Polyvinyl Chloride, Flexible (PVC, Flexible) | |
| Processing Method | Extrusion Coating | |
| Regional Availability | Africa & Middle East | |

| Descriptive Properties | Value | Comments |
|---------------------------------|---------------------------|--------------------------------------|
| | Asia Pacific | |
| | Europe | |
| | North America | |
| | South America | |
| Retention of Tensile Elongation | 84% | 100°C, 889.0 µm; 240 hr, UL Standard |
| Retention of Tensile Strength | 97% | 100°C, 889.0 µm; 240 hr, UL Standard |
| RoHS Compliance | RoHS Compliant | |
| Uses | Cable Jacketing | |
| | Wire & Cable Applications | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China