

PolyOne Geon™ Vinyl Wire & Cable W2301 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-W2301-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72	72	15 sec; ASTM D2240
Tensile Strength, Yield	13.8 MPa	2000 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	75.0 °C	167 °F	UL Temperature Rating
Brittleness Temperature	-40.0 °C	-40.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	154 - 166 °C	309 - 331 °F	

Descriptive Properties	Value	Comments
Additive	Lead Stabilizer	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion Coating	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	North America Value	Comments
	South America	
Uses	Communication Wire Jacketing	
	Wire & Cable Applications	
	Wire Jacketing	
Wire Types	CATV	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China