

PolyOne Geon™ Vinyl Wire & Cable W2407L Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-W2407L-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	83	83	15 sec; ASTM D2240
Tensile Strength, Yield	17.9 MPa	2600 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	300 %	300 %	Type IV, 510 mm/min; ASTM D638
Tensile Modulus	0.00896 GPa	1.30 ksi	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	60.0 °C	140 °F	UL Temperature Rating
Brittleness Temperature	-40.0 °C	-40.0 °F	ASTM D746
Oxygen Index	30 % @Thickness 1.91 mm	30 % @Thickness 0.0752 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 188 °C	360 - 370 °F	

Descriptive Properties	Value	Comments
Features	Flame Retardant	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion Coating	
Regional Availability	Africa & Middle East	

Descriptive Properties	Value	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Retention of Tensile Elongation	60%	100°C, 1.91 mm; 168 hr, UL Standard
RoHS Compliance	RoHS Compliant	
Uses	Communication Wire Jacketing	
	Wire & Cable Applications	
	Wire Jacketing	
Wire Types	CATV	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China