

PolyOne Geon™ Vinyl Wire & Cable WJLF112L Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-WJLF112L-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	77	77	15 sec; ASTM D2240
Tensile Strength, Yield	20.3 MPa	2940 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	350 %	350 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	75.0 °C	167 °F	UL Temperature Rating
Oxygen Index	27 % @Thickness 1.91 mm	27 % @Thickness 0.0752 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	163 - 168 °C	325 - 334 °F	

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	
Features	Flame Retardant	
	Good Surface Finish	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion Coating	
Regional Availability	Africa & Middle East	

Descriptive Properties	Value	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
RoHS Compliance	RoHS Compliant	
Uses	Communication Wire Insulation	
	Communication Wire Jacketing	
	Wire & Cable Applications	
Wire Types	CL2	
	CL2R	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China