

## PolyOne Gravi-Tech™ GRV-TP-080-W-NAT Styrene Butadiene Block Copolymer (SBC)

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Gravi-Tech-GRV-TP-080-W-NAT-Styrene-Butadiene-Block-Copolymer-SBC.php](http://www.lookpolymers.com/polymer_PolyOne-Gravi-Tech-GRV-TP-080-W-NAT-Styrene-Butadiene-Block-Copolymer-SBC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	7.98 g/cc	7.98 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	25	25	ASTM D2240
Tensile Strength, Yield	1.03 MPa	149 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	500 %	500 %	Type I, 5.1 mm/min; ASTM D638

Processing Properties	Metric	English	Comments
Melt Temperature	163 - 204 °C	325 - 399 °F	
Mold Temperature	15.6 - 37.8 °C	60.1 - 100 °F	
Drying Temperature	76.7 °C	170 °F	

Descriptive Properties	Value	Comments
Appearance	Natural Color	
Features	High Specific Gravity	
	Non-Toxic	
Forms	Pellets	
Generic Material	SBC	
Generic Name	Styrene Butadiene Block Copolymer (SBC)	
Processing Method	Injection Molding	
Regional Availability	Asia Pacific	
Uses	Industrial Applications	

Descriptive Properties	Value al/Healthcare Applications	Comments
	Projectiles	
	Sporting Goods	
	Weighting & Balancing	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China