

PolyOne Lubri-Tech™ AT-000/8T Acetal-Copolymer, PTFE Lubricated (discontinued **)

Category : Polymer , Thermoplastic , Acetal (POM)

Material Notes:

Description/Features:PTFE LubricatedInformation provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Lubri-Tech-AT-0008T-Acetal-Copolymer-PTFE-Lubricated-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D792
Water Absorption	0.15 % @Thickness 3.17 mm	0.15 % @Thickness 0.125 in	24 hr immersion; ASTM D570
Linear Mold Shrinkage	0.015 - 0.020 cm/cm	0.015 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	48.3 MPa	7000 psi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Elongation at Break	8.0 %	8.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	2.34 GPa	340 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.20 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	163 °C	325 °F	Unannealed, 0.125 in bars; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	104 °C	220 °F	Unannealed, 0.125 in bars; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China