

PolyOne Lubri-Tech™ BB-10GF/5T PC/ABS Blend, Glass Filled (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Glass Fiber Filled , Polycarbonate (PC)

Material Notes:

Description/Features: Glass Fiber Reinforced PolyOne First Choice Information provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Lubri-Tech-BB-10GF5T-PCABS-Blend-Glass-Filled-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.247 g/cc	1.247 g/cc	ASTM D792
Water Absorption	0.20 %	0.20 %	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0030 cm/cm	0.0020 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	5.31 GPa	770 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	93.1 MPa	13500 psi	ASTM D790
Flexural Modulus	5.31 GPa	770 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.50 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	232 - 277 °C	450 - 530 °F	Molding
Mold Temperature	>= 93.3 °C	>= 200 °F	
Drying Temperature	93.3 °C	200 °F	
Dry Time	2 hour	2 hour	

Descriptive Properties	Value	Comments
Product Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China