

PolyOne Lubri-Tech™ PF-30CF/15T Polysulfone, Carbon Fiber Reinforced, PTFE Lubricated (discontinued **)

Category : Polymer , Thermoplastic , Polysulfone (PSU)

Material Notes:

Description/Features: Carbon Fiber Reinforced PTFE Lubricated PolyOne First Choice Information provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Lubri-Tech-PF-30CF15T-Polysulfone-Carbon-Fiber-Reinforced-PTFE-Lubricated-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.472 g/cc	1.472 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	138 MPa	20000 psi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	11.7 GPa	1700 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	207 MPa	30000 psi	ASTM D790
Flexural Modulus	11.7 GPa	1700 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	2.00 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	177 °C	350 °F	Annealed, 0.125 in bars; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	10 - 100 ohm-cm	10 - 100 ohm-cm	ASTM D257
Surface Resistivity per Square	10 - 100 ohm	10 - 100 ohm	ASTM D257

Processing Properties	Metric	English	Comments
Melt Temperature	354 - 382 °C	670 - 720 °F	Molding

Processing Properties	Metric	English	Comments
Drying Temperature	135 - 149 °C	275 - 300 °F	
Dry Time	2 hour	2 hour	

Descriptive Properties	Value	Comments
Product Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China