

PolyOne Lubri-Tech™ PS-30GF/15T Polybutylene Terephthalate (PBT), Glass Filled, PTFE Lubricated (discontinued)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Description/Features: Glass Fiber Reinforced PTFE Lubricated PolyOne First Choice Information provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Lubri-Tech-PS-30GF15T-Polybutylene-Terephthalate-PBT-Glass-Filled-PTFE-Lubricated-nbspdiscontinued.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.63 g/cc	1.63 g/cc	ASTM D792
Water Absorption	0.040 %	0.040 %	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	103 MPa	15000 psi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.50 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	216 °C	420 °F	Annealed, 0.125 in bars; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Melt Temperature	243 - 271 °C	470 - 520 °F	Molding
Mold Temperature	65.6 - 107 °C	150 - 225 °F	
Drying Temperature	82.2 - 93.3 °C	180 - 200 °F	
Dry Time	2 hour	2 hour	

Descriptive Properties	Value	Comments
Product Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China