

PolyOne LubriOne™ ATH-000/05T Acetal (POM) Homopolymer (discontinued **)

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Homopolymer, Unreinforced

Material Notes:

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-LubriOne-ATH-00005T-Acetal-POM-Homopolymer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.43 g/cc	1.43 g/cc	ASTM D792
Water Absorption	0.010 % @Thickness 3.18 mm, Time 86400 sec	0.010 % @Thickness 0.125 in, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.010 - 0.020 cm/cm	0.010 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.2 MPa	8010 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	3.0 - 8.0 %	3.0 - 8.0 %	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	2.83 GPa	410 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	2.83 GPa	410 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	1.00 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A
Coefficient of Friction, Dynamic	0.40	0.40	vs. Steel; ASTM D1894
Coefficient of Friction, Static	0.27	0.27	vs. Steel; ASTM D1894

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	160 °C @Thickness 6.35 mm	320 °F @Thickness 0.250 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C @Thickness 6.35 mm	230 °F @Thickness 0.250 in	Unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	188 - 216 °C	370 - 421 °F	

Descriptive Properties	Value	Comments
Features	Good Wear Resistance	
	Homopolymer	
	Low Friction	
	Lubricated	
Forms	Pellets	
Generic Name	Acetal (POM) Homopolymer	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Appliance Components	
	Automotive Applications	
	Bearings	
	Business Equipment	
	Consumer Applications	
	Conveyor Parts	
	Gears	
	Industrial Applications	
	Printer Parts	
	Pulleys	
	Rollers	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China