

PolyOne LubriOne™ NN-000/15T Polyamide 66 (Nylon 66)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-LubriOne-NN-00015T-Polyamide-66-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792
Water Absorption	0.80 % @Thickness 3.18 mm	0.80 % @Thickness 0.125 in	@ 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.010 - 0.015 cm/cm	0.010 - 0.015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.5 MPa	9500 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	2.96 GPa	429 ksi	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	2.96 GPa	429 ksi	ASTM D790
Izod Impact, Notched	0.530 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	0.993 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A
Coefficient of Friction, Dynamic	0.43	0.43	vs. Steel - Dynamic; ASTM D1894
Coefficient of Friction, Static	0.25	0.25	vs. Steel - Static; ASTM D1894

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	232 °C @Thickness 6.35 mm	450 °F @Thickness 0.250 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.2 °C @Thickness 6.35 mm	180 °F @Thickness 0.250 in	Unannealed; ASTM D648
Flammability, UL94	HB	HB	UL 94

Processing Properties	Metric	English	Comments
Melt Temperature	277 - 304 °C	531 - 579 °F	
Mold Temperature	82.2 - 93.3 °C	180 - 200 °F	
Drying Temperature	71.1 - 76.7 °C	160 - 170 °F	
Dry Time	2.00 hour	2.00 hour	

Descriptive Properties	Value	Comments
Features	Good Wear Resistance	
	Low Friction	
	Lubricated	
Forms	Pellets	
Generic Material	Nylon 66	
Generic Name	Polyamide 66 (Nylon 66)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	South America	
RoHS Compliance	RoHS Compliant	
Uses	Appliance Components	
	Automotive Applications	
	Bearings	
	Business Equipment	
	Consumer Applications	
	Conveyor Parts	
	Gears	
	Industrial Applications	
	Printer Parts	

Descriptive Properties	Pulleys Value	Comments
Rollers		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China