

PolyOne Maxxam™ PPC-30T UV EXT 1148 Polypropylene Copolymer (PP Copolymer)

Category: Polymer, Thermoplastic, Polypropylene (PP), Polypropylene Copolymer

Material Notes:

PolyOne's Maxxam[™] family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Maxxam-PPC-30T-UV-EXT-1148-Polypropylene-Copolymer-PP-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 - 0.010 cm/cm	0.0060 - 0.010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments	
Tensile Strength, Yield	24.1 MPa	3500 psi	Type I, 51 mm/min; ASTM D638	
Elongation at Break	40 %	40 %	Type I, 51 mm/min; ASTM D638	
Flexural Strength	38.6 MPa	5600 psi	ASTM D790	
Flexural Modulus	2.34 GPa	339 ksi	ASTM D790	
Izod Impact, Notched	0.480 J/cm	0.899 ft-lb/in	Injection Molded; ASTM D256A	
	@Thickness 3.18 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F		

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa	118 °C	244 °F	Unannealed; ASTM D648
(66 psi)	@Thickness 3.18 mm	@Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Mold Temperature	16.0 - 50.0 °C	60.8 - 122 °F	

Descriptive Properties	Value	Comments
Additive	UV Stabilizer	
Appearance	Natural Color	



Descriptive Properties	Capelymer Value	Comments
	General Purpose	
	Good UV Resistance	
Filler / Reinforcement	Talc Filler, 30% Filler by Weight	
Forms	Pellets	
Generic Material	PP Copolymer	
Generic Name	Polypropylene Copolymer (PP Copolymer)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Automotive Applications	
	Construction Applications	
	Consumer Applications	
	General Purpose	
	Industrial Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China