

PolyOne Maxxam™ PPH-30T Nat Polypropylene Homopolymer (PP Homopolymer)

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Maxxam-PPH-30T-Nat-Polypropylene-Homopolymer-PP-Homopolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	31.7 MPa	4600 psi	Type I, 51 mm/min; ASTM D638
Elongation at Break	25 %	25 %	Type I, 51 mm/min; ASTM D638
Flexural Strength	53.1 MPa	7700 psi	ASTM D790
Flexural Modulus	3.72 GPa	540 ksi	ASTM D790
Izod Impact, Notched	0.320 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	0.599 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	127 °C @Thickness 3.18 mm	261 °F @Thickness 0.125 in	Annealed; ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	ALL; UL 94

Descriptive Properties	Value	Comments
Appearance	Natural Color	
Features	General Purpose	
	Homopolymer	
Filler / Reinforcement	Talc Filler	

Descriptive Properties	Value	Comments
Forms	Pellets	
Generic Material	PP Homopolymer	
Generic Name	Polypropylene Homopolymer (PP Homopolymer)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Automotive Applications	
	Construction Applications	
	Consumer Applications	
	General Purpose	
	Industrial Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China