

PolyOne Stat-Tech™ AS-10SS/000 ABS - 10% Stainless Steel Fiber (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Data provided by PolyOne.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Stat-Tech-AS-10SS000-ABS-10-Stainless-Steel-Fiber-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Water Absorption	0.15 % @Thickness 3.17 mm	0.15 % @Thickness 0.125 in	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	44.8 MPa	6500 psi	Type 1 - Rigids, Yield, 0.2 in/min; ASTM D638
Elongation at Break	1.0 - 3.0 %	1.0 - 3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	3.10 GPa	450 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	65.5 MPa	9500 psi	ASTM D790
Flexural Modulus	3.10 GPa	450 ksi	ASTM D790
Izod Impact, Notched	0.908 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.70 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	102 °C	215 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.0 - 100 ohm-cm	1.0 - 100 ohm-cm	ASTM D257
Surface Resistivity per Square	1.0 - 100 ohm	1.0 - 100 ohm	ASTM D257

Shielding Effectiveness Electrical Properties	30 - 60 dB Metric	30 - 60 dB English	1,000 MHz: PolyOne Internal Comments
Processing Properties	Metric	English	Comments
Melt Temperature	204 - 232 °C	400 - 450 °F	Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China