

## PolyOne Stat-Tech™ ST9620-0020 ES Red Liquid Crystal Polymer + PPS (LCP+PPS)

Category : Polymer , Thermoplastic , Liquid Crystal Polymer (LCP) , Polyphenylene Sulfide (PPS)

### Material Notes:

Stat-Tech™ Electrically Conductive Compounds are specifically engineered to provide anti-static, ESD and RFI/EMI shielding performance for critical electronic equipment applications. These compounds combine the performance of select engineering resins with reinforcing additives such as carbon powder, carbon fiber, nickel-coated carbon fiber and stainless steel fiber, for low to high levels of conductivity depending upon application requirements. Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Stat-Tech-ST9620-0020-ES-Red-Liquid-Crystal-Polymer-PPS-LCPPPS.php](http://www.lookpolymers.com/polymer_PolyOne-Stat-Tech-ST9620-0020-ES-Red-Liquid-Crystal-Polymer-PPS-LCPPPS.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.80 g/cc	1.80 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.014 - 0.015 cm/cm	0.014 - 0.015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	81.4 MPa	11800 psi	ASTM D638
Elongation at Break	0.75 %	0.75 %	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	116 MPa	16800 psi	ASTM D790
Flexural Modulus	12.4 GPa	1800 ksi	ASTM D790
Izod Impact, Notched	0.220 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	0.412 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	>= 245 °C	>= 473 °F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	10 - 1000 ohm-cm	10 - 1000 ohm-cm	ASTM D257
Surface Resistance	100 - 10000 ohm	100 - 10000 ohm	ASTM D257
Static Decay	0.0020 sec	0.0020 sec	(Mil-B-81705C), 12% RH, 5000kV to 50kV
	40 dB	40 dB	

Shielding Effectiveness Electrical Properties	Metric @Frequency 1.00e+9 Hz	English @Frequency 1.00e+9 Hz	1/8 thickness Comments
	55 dB	55 dB	1/8 thickness
	@Frequency 5.00e+9 Hz	@Frequency 5.00e+9 Hz	1/8 thickness
	61 dB	61 dB	1/8 thickness
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	1/8 thickness

Descriptive Properties	Value	Comments
Features	Electromagnetic Shielding (EMI)	
Filler / Reinforcement	Nickel-Coated Carbon Fiber	
Forms	Pellets	
Generic Material	LCP+PPS	
Generic Name	Liquid Crystal Polymer + PPS (LCP+PPS)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Aerospace Applications	
	Automotive Electronics	
	Computer Components	
	Connectors	
	Electrical Housing	
	Electrical/Electronic Applications	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**