

## PolyOne Synplast™ 9P-N Di Nonyl Phthalate

Category : Other Engineering Material , Additive/Filler for Polymer

### Material Notes:

Linear phthalate ester Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Synplast-9P-N-Di-Nonyl-Phthalate.php](http://www.lookpolymers.com/polymer_PolyOne-Synplast-9P-N-Di-Nonyl-Phthalate.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.962 - 0.968 g/cc	0.962 - 0.968 g/cc	ASTM D4052
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Kinematic Viscosity	46 cSt	46 cSt	ASTM D445
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Molecular Weight	420 g/mol	420 g/mol	Theoretical
Vapor Pressure	0.00133 bar	0.998 torr	
	@Temperature 200 °C	@Temperature 392 °F	
ASTM Color	25	25	Pt-Co Scale, Maximum; ASTM D1209

Thermal Properties	Metric	English	Comments
Pour Point	-50.0 °C	-58.0 °F	

Optical Properties	Metric	English	Comments
Refractive Index	1.48	1.48	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 0.10	<= 0.10	[mg KOH/g]; ASTM D1045

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.10 %	<= 0.10 %	ASTM D1533

Descriptive Properties	Value	Comments
Appearance	Clear, clean	ASTM D2090
	Clear/Transparent	
Ester Content	99%	ASTM D3465; Minimum

<b>Descriptive Properties</b> <small>Formic</small>	<b>Value</b> <small>Liquid</small>	<b>Comments</b>
Generic Material	Di Nonyl Phthalate	
Generic Name	Di Nonyl Phthalate	
Processing Method	Calendering	
	Compounding	
	Plastisol	
Regional Availability	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Automotive Applications	
	Automotive Interior Parts	
	Cable Jacketing	
	Film	
	Sheet	
	Wire & Cable Applications	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China